ARCHITECTURAL COLOR CHART

Kynar Finishes **Standard Colors**

KYNAR 500® HYLAR 5000® **LOW GLOSS**

- Final color selection should be made from actual color chips.
- For the most current information available, visit our website at www.aegiscopper.com
- See product catalog for gauge and color availability.
- All products available in smooth or embossed finish.
- Heavier gauges, narrower widths, striations and embossing minimize "oil canning."
- All Kynars & Metallic Kynars are low gloss colors.
- A 25-year limited paint warranty available for all colors upon written request, please inquire. (Outside the continental United States, please inquire.)



KYNAR Metallic

KYNAR 500® HYLAR 5000® **LOW GLOSS**



BRITE RED

SR .49 SRI 55

COPPER METALLIC * SR .45 SRI 51



HUNTER GREEN *

SR .35 SRI 39

SILVER METALLIC * SR .52 SRI 60

Note: Metallic coatings are directional. Panels and trim must be installed oriented in the same direction to prevent perceived shade variances. Directional arrows are on the back side of panels and trim to aid in the proper orientation.

♦ SIL-POLY Standard Colors

SILICONIZED POLYESTER Polar White is a Straight Polyester.



BURNISHED SLATE * SR .28 SRI 29



POLAR WHITE * SR .58 SRI 69



CLASSIC GREEN *

SR.28 SRI 30

CHARCOAL GRAY * SR.28 SRI 30



NATURAL PATINA

SR.41 SRI 47

LIGHT STONE * SR .50 SRI 58



RUSTIC RED * SR .36 SRI 40



KOKO BROWN * SR .28 SRI 30



FERN GREEN * SR .28 SRI 29



COAL BLACK * SR .30 SRI 31



HAWAIIAN BLUE * SR.32 SRI 35







🔅 What is

Solar Reflectivity (SR)?

Solar reflectivity or reflectance (SR) is the ability of a material to reflect solar energy from its surface back into the atmosphere. The SR value is a number

from 0 to 1.0. A value of 0 indicates that the material absorbs all solar energy and a value of 1.0 indicates it is all reflected. ENERGY STAR requires SR testing of both new and aged roof products. New products must have an SR value of 0.25 or higher for steep slope (above 2:12) roofing and an SR value of 0.65 or higher for low slope (2:12 or less) roofing. Aged testing takes 3 years to complete, so not all products that meet the initial requirements are qualified. For more information, please go to www.energystar.gov.



Solar Reflectance Index (SRI)?

The SRI is used to determine compliance with LEED requirements and is calculated according to ASTM E 1980 using values for reflectance and emissivity. Emissivity is a material's ability to release absorbed energy. To meet LEED requirements, a roofing material must have an SRI of 29 or higher for steep slope (above 2:12) roofing and an SRI value of 78 or higher for low slope (2:12 or less) roofing. For more information, please go to www.usgbc.org.

STANDARD KYNAR COLORS - SR & SRI Values

	on #	SNI#
HARBOR BLUE	.28	30
COLONIAL RED	.34	37
MEDIUM BRONZE	.33	36
PACIFIC BLUE	.29	31
HUNTER GREEN	.35	39
SNOW WHITE	.65	79
SLATE GRAY	.37	41
ALMOND	.63	76
MIDNIGHT BRONZE	.29	31
CLASSIC GREEN	.28	30
EVERGLADE	.33	36
BROWNSTONE	.47	54
TUNDRA	.46	53
SPRUCE	.36	40
NATURAL PATINA	.41	47
BRITE RED	.49	55

	SR #	SRI #
COPPER METALLIC	.45	51
SILVER METALLIC	.52	60

SIL-POLY COLORS - SR & SRI Values SR# SRI#

	=	=
BURNISHED SLATE	.28	29
POLAR WHITE	.58	69
CHARCOAL GRAY	.28	30
LIGHT STONE	.50	58
HAWAIIAN BLUE	.32	35
RUSTIC RED	.36	40
KOKO BROWN	.28	30
FERN GREEN	.28	29
COAL BLACK	.30	31